# Desulco<sup>®</sup> 9018




## **Product Type**

9018 is manufactured using Superior Graphite's proprietary electrothermal purification technology. This continuous high-temperature process exposes raw materials to extremely high temperatures so that impurities, including inorganic contaminants, are evaporated. 9018 is a fine narrow-sized graphitized desulfurized petroleum coke. Main uses are late addition in ladle of ductile iron and grey iron using cupola foundries when no mixing is occuring.

### **Product Characteristics**

- High Purity
- High Consistency
- Fast Dissolution
- Very Low Gas Content
- Low Sulfur Content
- Vitually Dust-Free
- High Wettability
- Strong Nucleation Properties





#### **Main Properties**

| Carbon         | >99.7%             |
|----------------|--------------------|
| Ash            | <0.3%              |
| Sulfur         | <0.03%             |
| Moisture       | <0.2%              |
| Size           | D50 = 0.32-0.36 mm |
| Real Density   | <1.8 g/cc          |
| Fe             | <25 ppm            |
| 0,             | <300 ppm           |
| H <sub>2</sub> | <30 ppm            |
| N <sub>2</sub> | <100 ppm           |
|                |                    |

#### **General Information**

| Formula       | Carbon     |
|---------------|------------|
| Chemical Name | Carbon     |
| CASNr         | 64743-05-1 |
| RoHS          | Certified  |
| REACH         | Exempted   |
|               |            |

#### **Standard Packaging**

| 25 kg Bags | 40 bags/pallet      |
|------------|---------------------|
| 50 lb Bags | 50 bags/pallet      |
| Bulk Bag   | 1000 kg bag/pallet  |
| Bulk Bag   | 2000 lbs bag/pallet |
|            |                     |

This Data Sheet is provided for informational purposes. Superior Graphite makes no express or implied representation or warranty regarding the accuracy of the information set forth in this Data Sheet or regarding any Superior Graphite product or the use thereof (including without limitation, any warranty of quality, merchantability, or fitness for a particular use or purpose), except to the extent otherwise expressly provided in Superior Graphite's Terms and Conditions of Sale. Each customer of Superior Graphite assumes all risk and liability relating to its use of Superior Graphite's products and is responsible for independently testing Superior Graphite's products prior to such customer's use thereof to determine whether such products are fit and suitable for such customer's intended use or purpose. This Data Sheet is subject to change upon written notice.